

4C4B (4-Coat4-Bake) Paint

General

4C4B paint finish gives the NSX/NSX-T a deep gloss and stunning finish. This manual provides information on paint defect repair and refinishing. Throughout, the objective has been to explain in a simple yet comprehensive manner the basic items you should know about paint repairs. Select the correct material for the defect and repaint or refinish in the correct manner as described in this manual.


⚠ WARNING

- Most paints contain substances that are harmful if inhaled or swallowed. Read the paint label before opening the container. Spray paint only in a well ventilated area.
- Cover spilled paint with sand, or wipe it up at once.
- Wear an approved respirator, gloves, eye protection and appropriate clothing when painting. Avoid contact with skin.
- If paint gets in your mouth or on your skin, rinse or wash thoroughly with water. If paint gets in your eyes, flush with water and get prompt medical attention.
- Paint is flammable. Store it in a safe place, and keep it away from sparks, flames or cigarettes.

Basic Rules in Repairing a 4C4B paint finish

To repair paint damage, always use the 2-part acrylic urethane paints designated; polish and bake each of the four coats, as in production, to maintain the original film thickness, and to assure the same quality as the original finish.

Outline of Factory Painting Process:



Features in Each Work Process

1. Pretreatment and Electrodeposition

In the pretreatment process, the entire body is degreased, cleaned, and coated with zinc phosphate by dipping after being. After the body has been cleaned with pure water, it is placed in an electrolytic bath of soluble primer (Cationic Electrodeposition). This produces a thorough corrosion inhibiting coating on the inner surfaces and corners of the body, pillars, sills or panel joints. Chipping primer is then applied to the most susceptible area (see page 8-13).

2. Intermediate coat 1

The intermediate coat 1 is applied to the prepared surface in for further protection against damages.

3. Intermediate coat 2

The intermediate coat is matched to the color of the top coat.

4. Top coat

Water base enamel paint and either polyester or acrylic resin paint is used in the top coat for higher solidity, smoothness, brightness, and weather resistance.

Sectional View of Paint Coats:

